

Information About *Molykote*[®] G-807 Low Friction Silicone Compound

Type

PTFE modified silicone compound

Physical Form

Light-consistency grease

Special Properties

Wide service temperature range; compatible with many plastic and rubber materials; good corrosion resistance; low friction properties

Primary Uses

Lubrication of metal/plastic and metal/rubber substrates in applications such as automotive ball joints, and brake caliper pins

Useful Temperature Range

-40° to 150°C (-40° to 302°F)

DESCRIPTION

Molykote[®] G-807 Low Friction Silicone Compound is a soft silicone compound containing specially formulated solid lubricants. It has excellent compatibility with plastics and rubber materials. It also has good corrosion resistance and low friction properties.

TYPICAL APPLICATIONS

Molykote G-807 Low Friction Silicone Compound is designed primarily for plastic/metal and metal/rubber lubrication in electromechanical applications such as automotive ball joints, and brake caliper pins.

HOW TO USE

Molykote G-807 Low Friction Silicone Compound can be applied using conventional grease application methods, including brush, grease gun, or automatic dispensing.

TYPICAL PROPERTIES

These values are not intended for use in preparing specifications.

Color	White
Penetration, unworked	300 to 330
Bleed, 24 hours at 150°C (302°F), maximum percent	0.5
Evaporation, 24 hours at 150°C (302°F), maximum percent	1.0
Melting Point	None
Specific Gravity	1.0

Specification Writers: Please obtain a copy of the Dow Corning Sales Specification for this product and use it as a basis for your specifications. It may be obtained from any Dow Corning Sales Office, or from Dow Corning Customer Service in Midland, MI. Call (517) 496-6000.

SHIPPING LIMITATIONS

None.

STORAGE AND SHELF LIFE

Molykote G-807 Low Friction Silicone Compound can be stored for 60 months from date of manufacture at ambient temperatures in its original, closed container.

Shelf life information is subject to change. Refer to the Sales Specification for current shelf life information.

PACKAGING

Molykote G-807 Low Friction Silicone Compound is available in 18-kg (40-lb) pails and 200-kg (440-lb) drums.

LIMITATIONS

Not intended for medical use.

SAFE HANDLING INFORMATION
PRODUCT SAFETY INFORMATION
REQUIRED FOR SAFE USE IS NOT
INCLUDED. BEFORE HANDLING,
READ PRODUCT AND MATERIAL
SAFETY DATA SHEETS AND CON-
TAINER LABELS FOR SAFE USE,
PHYSICAL AND HEALTH HAZARD
INFORMATION. THE MATERIAL
SAFETY DATA SHEET IS AVAILABLE
FROM YOUR DOW CORNING REP-
RESENTATIVE, OR DISTRIBUTOR,
OR BY WRITING TO DOW CORNING
CUSTOMER SERVICE, OR BY CALL-
ING 1-517-496-6000.

**LIMITED WARRANTY—
PLEASE READ CAREFULLY**

Dow Corning believes that the
information in this publication is an
accurate description of the typical
characteristics and/or uses of the
product or products, but it is your
responsibility to thoroughly test the
product in your specific application
to determine its performance, efficacy
and safety. Suggestions of uses should
not be taken as inducements to
infringe any particular patent.

Unless Dow Corning provides you with
a specific written warranty of fitness
for a particular use, Dow Corning's
sole warranty is that the product or
products will meet Dow Corning's
then current sales specifications.

**DOW CORNING SPECIFICALLY
DISCLAIMS ANY OTHER EXPRESS
OR IMPLIED WARRANTY, INCLUD-
ING THE WARRANTIES OF MER-
CHANTABILITY AND OF FITNESS
FOR USE.** Your exclusive remedy and
Dow Corning's sole liability for breach
of warranty is limited to refund of the
purchase price or replacement of any
product shown to be other than as
warranted, and Dow Corning expressly
disclaims any liability for incidental or
consequential damages.

Dow Corning and *Molykote* are registered trademarks
of Dow Corning Corporation.

©1997 Dow Corning Corporation.
All rights reserved.

Printed in USA AMPM0202/997 Form No. 10-761-97

Dow Corning Corporation
Midland, Michigan 48686-0994

DOW CORNING